Deep-blue perovskite single-mode lasing through efficient vapor-assisted chlorination

Joao M. Pina, Darshan H. Parmar, Golam Bappi, Chun Zhou, Hitarth Choubisa, Maral Vafaie, Amin M. Najarian, Koen Bertens, Laxmi Kishore Sagar, Yitong Dong, Yuan Gao, Sjoerd Hoogland, Makhsud I. Saidaminov, Edward H. Sargent

Version post-print

Citation J. M. Pina, D. H. Parmar, G. Bappi, C. Zhou, H. Choubisa, M. Vafaie, (published version) A. M. Najarian, K. Bertens, L. K. Sagar, Y. Dong, Y. Gao, S. Hoogland, M. I. Saidaminov, E. H. Sargent, Adv. Mater. 2021, 33, 2006697.

Publisher's Statement This is the peer reviewed version of the following article: J. M. Pina, D. H. Parmar, G. Bappi, C. Zhou, H. Choubisa, M. Vafaie, A. M. Najarian, K. Bertens, L. K. Sagar, Y. Dong, Y. Gao, S. Hoogland, M. I. Saidaminov, E. H. Sargent, Adv. Mater. 2021, 33, 2006697, which has been published in final form at <https://doi.org/10.1002/adma.202006697>. This article may be used for non-commercial purposes in accordance with Wiley Terms and Conditions for Use of Self-Archived Versions.

How to cite TSpace items

Always cite the published version, so the author(s) will receive recognition through services that track citation counts, e.g. Scopus. If you need to cite the page number of the **author manuscript from TSpace** because you cannot access the published version, then cite the TSpace version **in addition** to the published version using the permanent URI (handle) found on the record page.

This article was made openly accessible by U of T Faculty.
Please [tell us](#) how this access benefits you. Your story matters.

Deep-blue perovskite single-mode lasing through efficient vapor-assisted chlorination

Joao M. Pina¹, Darshan H. Parmar¹, Golam Bappi¹, Chun Zhou^{1,2}, Hitarth Choubisa¹, Maral Vafaie¹, Amin M. Najarian¹, Koen Bertens¹, Laxmi Kishore Sagar¹, Yitong Dong¹, Yuan Gao¹, Sjoerd Hoogland¹, Makhsud I. Saidaminov^{1,3} and Edward H. Sargent^{,1}*

¹The Edward S. Rogers Department of Electrical and Computer Engineering, University of Toronto, Toronto, Ontario M5S 3G4, Canada

²Key Laboratory of Materials for High-Power Laser, Shanghai Institute of Optics and Fine Mechanics, Chinese Academy of Sciences, Shanghai 201800, China

³Present address: Department of Chemistry and Electrical & Computer Engineering, Centre for Advanced Materials and Related Technologies (CAMTEC), University of Victoria, Victoria, British Columbia V8P 5C2, Canada

Keywords: lasing; perovskite; deep-blue; halide exchange; vertical-cavity surface-emitting laser

Metal halide perovskites have emerged as promising candidates for solution-processed laser gain materials, with impressive performance in the green and red spectral regions. Despite exciting progress, deep-blue – an important wavelength for laser applications – remains underexplored: indeed cavity integration and single-mode lasing from large-bandgap perovskites have yet to be achieved. Here we report a vapor-assisted chlorination strategy that enables synthesis of low-dimensional CsPbCl₃ thin films exhibiting deep-blue emission. Using this approach, we achieve high quality perovskite thin films having a low surface roughness (RMS ~ 1.3 nm) and efficient charge transfer properties. These enable us to document low-

threshold amplified spontaneous emission (ASE). Levering the high quality of the gain medium, we fabricate vertical-cavity surface-emitting lasers with a low lasing threshold of 6.5 $\mu\text{J}/\text{cm}^2$. This report of deep-blue perovskite single-mode lasing showcases the prospect of increasing the range of deep-blue laser sources.

The active gain medium of a semiconductor laser diode is often comprised of a multiple quantum well (QW) structure grown through expensive epitaxial methods such as chemical vapor deposition or molecular beam epitaxy.^[1] These layered heterostructures provide carrier and electromagnetic field confinement due to bandgap and refractive index contrast between the quantum well and the surrounding cladding layers, leading to decreased thresholds and improved laser action.^[1,2]

Reduced-dimensional metal halide perovskites (RDPs) are self-assembled solution-based natural quantum wells with the chemical formula of $A'_2A_{n-1}M_nX_{3n+1}$, with A' commonly being a long organic cation (such as $C_4H_{12}N^+$ [BA^+] and $C_8H_{12}N^+$ [PEA^+]), A a smaller size cation (such as $CH_3NH_3^+$ [MA^+] and Cs^+), M a divalent metal cation (such as Pb^{2+} and Sn^{2+}) and X a halide (Cl^- , Br^- or I^-).^[3,4,5] The large A' organic molecule, usually long-chain aliphatic or aromatic alkylammonium cations, provides the large bandgap, low permittivity and low refractive index to achieve the contrast required to confine generated excitons and electromagnetic field within the inorganic octahedral cages composing the perovskite.

As in epitaxially-grown QWs, solution-based RDPs achieve increased exciton binding energy and overall optical oscillator strengths.^[4,6] The degree of exciton confinement within the well is determined by the number (n) of octahedral monolayers enclosed by the large organic cations. The contrasting bandgap and band alignment between the different wells provides an energy gradient which leads to charge transfer towards smaller bandgap domains.^[7,8] The hydrophobic nature of the A' cation improves the overall device stability under ambient conditions, increasing the viability of the material as a candidate for optoelectronic applications.^[9] Stronger optical oscillator strength, faster population inversion via energy transfer along quantum wells and improved stability make RDPs attractive solutions for laser devices.

Laser action and amplified spontaneous emission (ASE) using RDPs as an active gain media have been demonstrated in the green and red spectral regions.^[3,4,5,10,11] Fast energy transfer along quantum wells concentrates photogenerated carriers in the lowest-bandgap domain, leading to fast population inversion and stimulated emission. This leads to gain coefficients in RDPs exceeding those of their 3D counterparts,^[3,5] and stable laser action for more than ten hours.^[4,5] However, cavity integration and lasing from large-bandgap RDPs have not been achieved even though deep-blue lasing emission is of considerable interest in lithography, high-density data storage, and medical and scientific devices. Reports of deep-blue perovskite lasing are limited to nanowires^[12,13] and microcubes^[14,15] which have inherent device integration problems. This gap is largely due to thin-film synthesis difficulties and energetically favorable deep traps in wide-bandgap semiconductors: on the one hand, low solubility of chloride-based precursors^[16] aggravates the fabrication of films which are essential for cavity integration; on the other hand, chloride vacancies introduce trap states within the bandgap^[17] leading to increased non-radiative recombination rates and overall low photoluminescence quantum yields (PLQYs).

In this work, we demonstrate room-temperature single-mode deep-blue ASE and lasing using $(\text{BA})_2\text{Cs}_{n-1}\text{Pb}_n\text{Cl}_{3n+1}$. The low solubility of chloride-based precursors relative to bromide and iodide counterparts leads to lower film-quality. To overcome this difficulty, we developed an efficient vapor-assisted post-synthesis chlorination procedure to fully convert high-quality green-emitting $(\text{BA})_2\text{Cs}_{n-1}\text{Pb}_n\text{Br}_{3n+1}$ into chloride-based perovskite films with a surface roughness of less than 1.5 nm (root-mean-square, RMS), efficient charge transfer and low-threshold ASE. A vertical-cavity surface-emitting laser (VCSEL) consisting of two distributed Bragg reflectors (DBRs) and a high-quality $(\text{BA})_2\text{Cs}_5\text{Pb}_6\text{Cl}_{19}$ film is fabricated to achieve deep-blue (425 nm) room-temperature single-mode lasing with a threshold of 6.5 $\mu\text{J}/\text{cm}^2$.

Figure 1. Chloride-based films synthesized using previously reported methods. a) Solubility of inorganic iodide, bromide and chloride precursors in DMSO. b) AFM height image of $(\text{BA})_2\text{Cs}_5\text{Pb}_6\text{Cl}_{19}$ film using 1-step synthesis method (RMS ~ 7.6 nm). c) AFM height image of $(\text{BA})_2\text{Cs}_5\text{Pb}_6\text{Cl}_{19}$ film using 2-step synthesis method (RMS ~ 36.2 nm). d) Formation energy calculations for iodide, bromide and chloride-based perovskites. The inset shows the chemical equation of the halide exchange reaction of $(\text{BA})_2\text{Cs}_{n-1}\text{Pb}_n\text{Br}_{3n+1}$ to $(\text{BA})_2\text{Cs}_{n-1}\text{Pb}_n\text{Cl}_{3n+1}$.

Previous works on green and red-emitting RDPs were based on the small monovalent CH_3NH_3^+ (MA^+) occupying the A cation position in the perovskite structure.^[3,4,11] However, MA-BX_3 single crystals, polycrystalline films and quantum-confined structures showed outstanding performances only within the green and red-emitting spectral range (with bromide and iodide occupying the halide position). Room temperature stimulated emission in the form of lasing or ASE was not achieved with MAPbCl_3 , presumably owing to the high trap density in this material.^[18,19] As such, cesium (Cs) was chosen to occupy the A-site position of the perovskite

structure. A larger organic cation, such as butylammonium (BA, $\text{C}_4\text{H}_9\text{NH}_3^+$), is used to bisect the 3D perovskite lattice along one axis to form $(\text{BA})_2\text{Cs}_{n-1}\text{Pb}_n\text{Cl}_{3n-1}$. The low solubility in dimethylsulfoxide (DMSO) of chloride-based precursors relative to bromide and iodide counterparts is shown in Figure 1a. Other commonly used organic solvents such as dimethylformamide (DMF) and γ -butyrolactone (GBL) reached saturation with even lower precursor concentrations. The maximum achievable chloride-based precursor solution concentration (which includes BaCl_2 , PbCl_2 and CsCl) is limited by the solubility of CsCl , of approximately 0.07 M in DMSO.

The standard approach for bromide-based and iodide-based perovskite film fabrication relies on spin-coating, with an intermediate anti-solvent dripping step which leads to perovskite crystallization (Figure S1, Supporting Information). The same technique applied to chloride-based perovskites leads to high surface roughness ($\text{RMS} \sim 7.6 \text{ nm}$) and high peak-to-valley height variations of the perovskite film (Figure 1b). Due to the low solubility of the precursors, little can be dissolved before reaching solvent saturation. The subsequent evaporation of the saturated solvent during the spinning step leads to unwanted precursor precipitation and perovskite formation. Other film-fabrication methodologies, such as a 2-step approach (Figure S2, Supporting Information), led to equally large surface roughness and peak-to-valley height variation (Figure 1c). This method often leads to large grain sizes^[20,21,22] which increase optical propagation losses due to scattering at the grain boundaries.

To circumvent the difficulties in synthesizing high-quality chloride-based perovskite films, other approaches were considered. Chloride-based perovskites have the lowest formation energy compared to their bromide and iodide counterparts, a trend that is especially evident in CsPbX_3 (Figure 1d). We hypothesized that if a bromide-based perovskite film is synthesized, the significantly lower formation energy of chloride-based perovskites would allow for an

efficient halide exchange (bromide for chloride) process when in contact with a chloride-source such as HCl (following the chemical reaction shown in the inset of Figure 1d). Furthermore, since the building blocks composing the perovskite are already in place, exchanging chlorides for bromides would not diminish the surface quality of the film. Halide exchange in perovskite nanocrystals has been previously demonstrated.^[23,24] Less extensively studied is halide exchange in pre-synthesized polycrystalline films, where prior methods have come at the cost of a large surface-roughness and poor optoelectronic properties.^[25,26]

Figure 2. Vapor-assisted chlorination for the fabrication of high-quality blue-emitting films. a) Schematic of the set-up used for vapor-assisted chlorination. b) Absorption profile variation as a function of the chlorination time. c) Wavelength position of $n=1$ and $n=2$ excitonic peaks and 3D absorption-edge as a function of chlorination time. d) XRD peaks before and after the chlorination process. e-f) AFM height image of a bromide-based perovskite film before (RMS ~ 1.8 nm) and after the chlorination process (RMS ~ 1.3 nm). g) PLE and PL of a fully-converted film showing emission at 415 nm. h) Schematic of the energy transfer process within layered perovskites towards smaller bandgap domains. i) Optical constants obtained by ellipsometry.

Hydrochloric acid (HCl, 12M) is bubbled using N_2 or argon as a carrier gas through the sample chamber (Figure 2a). Prior to reaching the sample chamber, the vapor is passed through a desiccation chamber to remove most of the water content of the gas; moisture is shown to diminish film morphology and optical properties of the synthesized film. Halide exchange was

not achieved in 2D perovskites (Figure S3, Supporting Information); while, with the presence of inorganic cesium, partial and complete anion-exchange are achieved in RDPs. In contrast with prior reports, the exchange process is carried out at room temperature and does not require further annealing. This is due to the favorable low-formation energy of chloride-based perovskites. Figure 2b shows the absorption spectra variation with increasing chlorination time. The excitonic peaks corresponding to $n = 1$ and $n = 2$ quantum wells and the band-edge correspondent to the 3D domains of the material blue-shift from a full-bromide perovskite to the position expected for a full-chloride perovskite (Figure 2c). The final peaks are approximately 100 nm blue-shifted from the initial bromide-film, demonstrating an efficient exchange process. X-ray diffraction (XRD) peaks corresponding to $n = 1$ [100], $n = 2$ [200] and $n = \infty$ (3D domain) [100] obtained after chlorination show a clear shift towards higher angles (Figure 2d), consistent with the smaller lattice constant of chloride-based perovskites.

For a stoichiometry of $\langle n \rangle = 6$, high-quality green-emitting films synthesized using a standard methodology (Figure S1, Supporting Information) are obtained with RMS ~ 1.8 nm and peak-to-valley height variations below 20 nm (Figure 2e). In contrast to directly synthesized chloride-based films (Figure 1b-c), through vapor-assisted chlorination of bromide-based perovskites, a fully-chloride perovskite film can be obtained with RMS ~ 1.3 nm (Figure 2f). The surface morphology improvement is attributed to the chlorination process which isotropically etches the surface roughness features of the film (Figure S4, Supporting Information). Figure 2g shows a photoluminescence-excitation (PLE) and photoluminescence (PL) spectra of the fully-converted film showing emission at around 410 nm. The PLE spectrum shows an increased rate emission at excitation wavelengths lower than 370 nm and 355 nm, corresponding to the position of the $n = 2$ and $n = 1$ excitonic peak, respectively. The increased photoluminescence intensity as a function of the excitation wavelength with a well-defined single emission peak demonstrates the efficient charge transfer mechanism between

quantum wells with various n values. Figure 2h shows a schematic of the transfer mechanism with carrier funneling from large bandgap (highly confined) to lower bandgap domains. The real and imaginary parts of the dielectric function (Figure 2i) show several features corresponding to the differently sized wells. The high refractive index within the wavelength range of light emission ($n \sim 2.4$) suggests that substantial modal confinement can be achieved with RDPs thin-films. This is an advantage over other solution-based quantum-confined structures such as quantum dots, whose refractive index is approximately $n \sim 2$.^[27,28]

Figure 3. Amplified spontaneous emission from 250 fs pulsed excitation in perovskite films before and after the vapor-assisted chlorination process. a) Wavelength-tunability of ASE controlled by chlorination time. b-c) ASE spectra and power-dependent PL of a $\langle n \rangle = 6$ perovskite film before and after halide exchange. d) ASE threshold comparison before $((\text{BA})_2\text{Cs}_{n-1}\text{Pb}_n\text{Br}_{3n+1})$ and after $((\text{BA})_2\text{Cs}_{n-1}\text{Pb}_n\text{Cl}_{3n+1})$ halide exchange for different average n values.

By controlling the anionic stoichiometry through means of chlorination time, the ASE peak position can be tuned within a range of 100 nm (Figure 3a). Images of the films used for ASE measurements are shown in Figure S5, Supporting Information. We optimized the initial synthesis conditions and stoichiometry of bromide-based films to achieve a green-emitting ASE threshold of $7.2 \mu\text{J}/\text{cm}^2$, as shown in Figure 3b.

The deep-blue ASE spectra and power-dependent PL of the films after chlorination is shown in Figure 3c. As expected, the threshold is increased in comparison with the green-emitting

perovskite films. Due to the increased bandgap of chloride perovskites in comparison with bromide and iodide counterparts, halogen vacancies lead to trap-states occupying deeper energies within the bandgap, therefore increasing the rate of non-radiative recombination.^[17] Furthermore, the chlorination process reduces the film thickness by a factor of 2 (Figure S6, Supporting Information). This decreases the modal confinement of emitted light by approximately 20% which further increases the ASE threshold (Figure S7, Supporting Information). Consistent with previous green-emitting RDPs reports,^[4] the lowest achieved ASE threshold is obtained for a stoichiometry of $\langle n \rangle = 6$. The curved profile of Figure 3d demonstrates that precise control of stoichiometry is required to achieve low-threshold ASE. A 3D perovskite ($n = \infty$) has high modal gain, however, it can be improved in an RDP form due to the improved film morphology and faster population inversion via energy transfer along quantum wells. In the limit of $n = 1$ (2D perovskite), stimulated emission is not achieved due to strong electron-phonon interactions which provide the required momentum for band-edge-to-trap processes,^[29] leading to free exciton trapping and bound biexciton formation pathways that effectively compete with biexcitonic gain.^[30] This leads to a higher ASE threshold for $\langle n \rangle = 4$ green-emitting perovskites and no ASE was obtained after the chlorination process.

Figure 4. Low-threshold lasing from 250 fs pulsed excitation using a VCSEL structure. a) Schematic of the $(\text{BA})_2\text{Cs}_5\text{Pb}_6\text{Cl}_{19}$ VCSEL. b) Transmission spectrum of the DBR mirror: excitation and lasing wavelengths are shown with a dashed line. c) Power-dependent emission spectra from the perovskite VCSEL. Inset shows a far-field image of the device's emission with pumping intensity above the lasing threshold (scale bar of 500 μm). d) Lasing spectra with reduced FWHM (limited by spectrometer resolution). e) Integrated power-dependent PL as a function of excitation fluence, showing a lasing threshold of 6.5 $\mu\text{J}/\text{cm}^2$.

A vertical-cavity surface-emitting laser was built using a 70 nm $(\text{BA})_2\text{Cs}_5\text{Pb}_6\text{Cl}_{19}$ film placed between two high-reflectivity ($> 99.8\%$) DBR mirrors, as shown in Figure 4a. The DBR transmission spectrum (Figure 4b) shows a stop-band which encloses the emission wavelength of the film. The excitation wavelength was set to 337 nm which falls into a high transmission fringe of the DBR. Excitation was applied normal to the bottom DBR mirror and the emission was collected normal to the top DBR mirror (Figure S8, Supporting Information). Figure 4c shows the PL spectra at different pump fluences. Room-temperature single-mode lasing is

achieved with a full-width half-maximum (FWHM) of 1.35 nm (Figure 4d). This is an upper-bound value since it is limited by the spectrometer resolution, but represents a clear reduction relative to the SE FWHM (~ 13 nm). Power-dependent PL (Figure 4e) shows a clear threshold at around $6.5 \mu\text{J}/\text{cm}^2$ followed by an output-power increase of two to three orders of magnitude. Below threshold, broader PL due to spontaneous emission is obtained (Figure S9, Supporting Information). An image of the transparent device is shown in Figure S10, Supporting Information. One property of lasing is that the emission wavelength will be characteristic of the specific gain medium and resonator cavity length.^[31] By slightly misaligning the position of the top DBR with respect to the bottom DBR, therefore changing the path-length between the mirrors, resonances centered at different wavelengths are obtained, showing that the lasing wavelength can be tuned with cavity length. This is shown in Figure S11, Supporting Information. This helps to differentiate ASE from true laser operation since ASE is not influenced by the resonator characteristics.^[31]

In summary, thin-film deep-blue amplified spontaneous emission and single-mode lasing are achieved at room temperature in perovskites for the first time. We found that vapor-assisted chlorination of green-emitting bromide-based perovskite films is a viable route towards high-quality fully-chloride-based perovskite films. This strategy circumvents the difficulties in producing high-quality chloride-based films due to the inherent low solubility of the precursors. Films of $(\text{BA})_2\text{Cs}_5\text{Pb}_6\text{Cl}_{19}$ suitable for cavity integration (RMS ~ 1.3 nm) were used to fabricate a vertical-cavity surface-emitting laser. Low-threshold ($6.5 \mu\text{J}/\text{cm}^2$) single-mode lasing was achieved at room temperature in ambient conditions showing the feasibility of the proposed approach.

Experimental Section

Materials and chemicals: Cesium bromide (CsBr), lead bromide (PbBr₂) and dimethylsulfoxide (DMSO) were purchased from Sigma-Aldrich. Butylammonium bromide (BABr) was purchased from GreatCell Solar. Chloroform was purchased from DriSolv. Hydrochloric acid (HCl) (37 %) was purchased from Caledon Laboratory Chemicals. All chemicals were used as received.

Bromide-based RDP thin-film fabrication: The precursor solution was prepared by dissolving stoichiometric quantities of PbBr₂ (0.5 M), CsBr and BABr in DMSO under continuous stirring for 1 h at room temperature. Glass substrates were O₂ plasma-treated to improve adhesion. The precursor solution was spin-coated onto the substrates via a two-step process: 1000 rpm for 10 s and 5000 r.p.m. for 60 s. During the second spin step, 1 mL of chloroform was poured onto the substrate. The films were then annealed at 95 °C for 7.5 min. All the samples were prepared in a glove box with N₂ atmosphere in order to control the atmospheric conditions, however, similar results were obtained when the preparation was done under ambient conditions.

Chloride-based RDP thin-film fabrication: Bromide-based RDP films were introduced into the sample chamber in a home-built vapor transport system. HCl was bubbled using N₂ or argon through the sample chamber (of approximately 90 cm³). The vapor is passed through a desiccation chamber to remove most of the water content of the gas. Conversion time was dependent on the degradation state of the HCl and gas flow.

VCSEL fabrication: Two commercially available DBRs (R[0° , 370 - 425 nm] > 99.8 %) were purchased from LayerTec Optical Coating. A bromide-based RDP thin-film was spun onto one DBR according to the procedure described in *Bromide-based RDP thin-film fabrication*. Further on, the bromide-based film was halide exchanged using the procedure described in

Chloride-based RDP thin-film fabrication. The two DBRs were then aligned using the optical setup shown in Figure S8, Supporting Information.

Structural characterizations: X-ray diffractograms were recorded using a Rigaku MiniFlex 600 powder X-ray diffractometer equipped with a NaI scintillation counter and using monochromatized Cu K α radiation ($\lambda=1.5406\text{\AA}$).

Optical measurements: UV–Vis absorption was measured using a Perkin Elmer LAMBDA 950 UV/Vis/NIR spectrometer; in the measurement, light is transmitted through the film, thus simultaneously providing absorption contributions of the surface and the interior of the film. PL and PLE spectra were recorded using a Horiba Fluorolog system using a Xe lamp as the excitation source. Ellipsometry measurements were performed using Horiba Jobin Yvon UVISSEL Ellipsometer. The obtained data was fitted using DeltaPsi2. The films were treated as substrates with optical constants defined by a Kramers-Kronig consistent series of Voigt oscillators.

ASE and lasing measurements: Samples were optically excited using a 340 nm (337 nm for lasing measurements) femtosecond laser source with a repetition rate of 1000 Hz. The laser source consisted of a Yb:KGW regenerative amplifier (Pharos, Light Conversion) with 1030 nm fundamental which is passed through an optical parametric amplifier (Orpheus, Light Conversion) to generate the 340 nm pump light pulse. The spectral data was collected using a UV-vis USB 2000+ spectrometer (Ocean Optics). A multi-mode fiber was used to collect all spectral data, except for the data presented in Figure 4d, which was collected with a single-mode fiber allowing a maximum resolution of ~ 1.4 nm. During laser characterization measurements, due to the low photon fluence available below threshold, we acquired three measurements per fluence and used only the fluence datapoints with the same integrated intensity.

AFM measurements: Surface morphology was characterized using an Asylum Research Cypher operating in tapping mode. The data was analyzed using WSxM software.^[32]

First-principle calculations: Formation energies were obtained using first principle Density Functional Theory (DFT) calculations. Using Perdew-Burke-Ernzerhof (PBE) functional as implemented in VASP, total energies of the systems were calculated on a k-points grid of size 3x3x2 and centered at Gamma. Formation energies were further calculated with respect to standard states of constituent elements which were then normalized to formation energy per atom. Pymatgen^[33] phase diagram was used to query Materials Project^[34] database to first benchmark the obtained formation energy results for MAPbI₃. With consistent benchmarking settings, the formation energies were calculated for the rest of the compositions.

Acknowledgements

This work was supported financially by the R&D Center U.S., San Jose Laboratory, A Division of Sony Corporation of America (2018 Sony Research Award Program Ref# 2019-0669). The authors acknowledge the members of the R&D Center in Japan, from Sony Corporation, for fruitful discussions. The authors thank Dr. Grant Walters for guidance in ellipsometry data analysis.

References

- [1] L. A. Coldren, S. W. Corzine, M. L. Mashanovitch, *Diode Lasers and Photonic Integrated Circuits, 2nd Edition*, John Wiley & Sons, **2012**.
- [2] H. C. Casey, M. B. Panish, *Heterostructure Lasers*, Academic Press, New York (Etc.), **1978**.
- [3] M. Li, Q. Wei, S. K. Muduli, N. Yantara, Q. Xu, N. Mathews, S. G. Mhaisalkar, G. Xing, T. C. Sum, *Advanced Materials* **2018**, 30, 1707235.
- [4] H. Zhang, Q. Liao, Y. Wu, Z. Zhang, Q. Gao, P. Liu, M. Li, J. Yao, H. Fu, *Advanced Materials* **2018**, 30, 1706186.
- [5] M. Li, Q. Gao, P. Liu, Q. Liao, H. Zhang, J. Yao, W. Hu, Y. Wu, H. Fu, *Advanced Functional Materials* **2018**, 28, 1707006.
- [6] X. Hong, T. Ishihara, A. V. Nurmikko, *Physical Review B* **1992**, 45, 6961.

- [7] J. Xing, Y. Zhao, M. Askerka, L. N. Quan, X. Gong, W. Zhao, J. Zhao, H. Tan, G. Long, L. Gao, Z. Yang, O. Voznyy, J. Tang, Z.-H. Lu, Q. Xiong, E. H. Sargent, *Nature Communications* **2018**, 9, 3541.
- [8] G. Xing, B. Wu, X. Wu, M. Li, B. Du, Q. Wei, J. Guo, E. K. L. Yeow, T. C. Sum, W. Huang, *Nature Communications* **2017**, 8, 14558.
- [9] H. Zheng, G. Liu, L. Zhu, J. Ye, X. Zhang, A. Alsaedi, T. Hayat, X. Pan, S. Dai, *Advanced Energy Materials* **2018**, 8, 1800051.
- [10] J. Guo, T. Liu, M. Li, C. Liang, K. Wang, G. Hong, Y. Tang, G. Long, S.-F. Yu, T.-W. Lee, W. Huang, G. Xing, *Nature Communications* **2020**, 11, 3361.
- [11] M. R. Leyden, T. Matsushima, C. Qin, S. Ruan, H. Ye, C. Adachi, *Physical Chemistry Chemical Physics* **2018**, 20, 15030.
- [12] Y. Fu, H. Zhu, C. C. Stoumpos, Q. Ding, J. Wang, M. G. Kanatzidis, X. Zhu, S. Jin, *ACS Nano* **2016**, 10, 7963.
- [13] S. W. Eaton, M. Lai, N. A. Gibson, A. B. Wong, L. Dou, J. Ma, L.-W. Wang, S. R. Leone, P. Yang, *Proceedings of the National Academy of Sciences* **2016**, 113, 1993.
- [14] Z. Hu, Z. Liu, Y. Bian, D. Liu, X. Tang, W. Hu, Z. Zang, M. Zhou, L. Sun, J. Tang, Y. Li, J. Du, Y. Leng, *Advanced Optical Materials* **2017**, 5, 1700419.
- [15] X. He, P. Liu, H. Zhang, Q. Liao, J. Yao, H. Fu, *Advanced Materials* **2017**, 29, 1604510.
- [16] H. Wang, X. Zhao, B. Zhang, Z. Xie, *Journal of Materials Chemistry C* **2019**, 7, 5596.
- [17] A. Buin, R. Comin, J. Xu, A. H. Ip, E. H. Sargent, *Chemistry of Materials* **2015**, 27, 4405.

- [18] G. Xing, N. Mathews, S. S. Lim, N. Yantara, X. Liu, D. Sabba, M. Grätzel, S. Mhaisalkar, T. C. Sum, *Nature Materials* **2014**, 13, 476.
- [19] H. Zhu, Y. Fu, F. Meng, X. Wu, Z. Gong, Q. Ding, M. V. Gustafsson, M. T. Trinh, S. Jin, X.-Y. Zhu, *Nature Materials* **2015**, 14, 636.
- [20] A. Bahtiar, S. Rahmanita, Y. D. Inayatle, IOP Conference Series: *Materials Science and Engineering* **2017**, 196, 012037.
- [21] K. Liang, D. B. Mitzi, M. T. Prikas, *Chemistry of Materials* **1998**, 10, 403.
- [22] B. R. Sutherland, S. Hoogland, M. M. Adachi, C. T. O. Wong, E. H. Sargent, *ACS Nano* **2014**, 8, 10947.
- [23] G. Nedelcu, L. Protesescu, S. Yakunin, M. I. Bodnarchuk, M. J. Grotevent, M. V. Kovalenko, *Nano Letters* **2015**, 15, 5635.
- [24] Q. A. Akkerman, V. D’Innocenzo, S. Accornero, A. Scarpellini, A. Petrozza, M. Prato, L. Manna, *Journal of the American Chemical Society* **2015**, 137, 10276.
- [25] S. E. Creutz, E. N. Crites, M. C. D. Siena, D. R. Gamelin, *Chemistry of Materials* **2018**, 30, 4887.
- [26] A. Pushkarev, V. Korolev, S. Anoshkin, F. Komissarenko, S. Makarov, A. Zakhidov, *Journal of Physics: Conference Series* **2018**, 1092, 012122.
- [27] M. M. Adachi, F. Fan, D. P. Sellan, S. Hoogland, O. Voznyy, A. J. Houtepen, K. D. Parrish, P. Kanjanaboos, J. A. Malen, E. H. Sargent, *Nature Communications* **2015**, 6, 8694.
- [28] J. Roh, Y.-S. Park, J. Lim, V. I. Klimov, *Nature Communications* **2020**, 11, 271.

- [29] X. Gong, O. Voznyy, A. Jain, W. Liu, R. Sabatini, Z. Piontkowski, G. Walters, G. Bappi, S. Nokhrin, O. Bushuyev, M. Yuan, R. Comin, D. Mccamant, S. O. Kelley, E. H. Sargent, *Nature Materials* **2018**, 17, 550.
- [30] W. K. Chong, K. Thirumal, D. Giovanni, T. W. Goh, X. Liu, N. Mathews, S. Mhaisalkar, T. C. Sum, *Physical Chemistry Chemical Physics* **2016**, 18, 14701.
- [31] I. D. W. Samuel, E. B. Namdas, G. A. Turnbull, *Nature Photonics* **2009**, 3, 546.
- [32] I. Horcas, R. Fernández, J. M. Gómez-Rodríguez, J. Colchero, J. Gómez-Herrero, A. M. Baro, *Review of Scientific Instruments* **2007**, 78, 013705.
- [33] S. P. Ong, W. D. Richards, A. Jain, G. Hautier, M. Kocher, S. Cholia, D. Gunter, V. L. Chevrier, K. A. Persson, G. Ceder, *Computational Materials Science* **2013**, 68, 314.
- [34] A. Jain, S. P. Ong, G. Hautier, W. Chen, W. D. Richards, S. Dacek, S. Cholia, D. Gunter, D. Skinner, G. Ceder, K. A. Persson, *APL Materials* **2013**, 1, 011002.