Canadian Geotechnical Journal
Revue canadienne de géotechnique

**Multi-scale Laboratory Evaluation of the Physical,
Mechanical and Microstructural Properties of Soft Highway
Subgrade Soil Stabilized with Calcium Carbide Residue**

Journal:	<i>Canadian Geotechnical Journal</i>
Manuscript ID	cgj-2015-0245.R1
Manuscript Type:	Article
Date Submitted by the Author:	13-Aug-2015
Complete List of Authors:	Jiang, Ning-Jun; University of Cambridge, Department of Engineering Du, Yan-Jun; Southeast University, Institute of Geotechnical Engineering Liu, Songyu; Southeast University, Institute of Geotechnical Engineering Wei, Ming-Li; Southeast University, Institute of Geotechnical Engineering Horpibulsuk, Suksun; Suranaree University of Technology, Civil Engineering Arulrajah, Arul; Swinburne University of Technology
Keyword:	calcium carbide residue, multi-scale, pozzolanic reaction, soil stabilization

SCHOLARONE™
Manuscripts

**Multi-scale Laboratory Evaluation of the Physical, Mechanical and Microstructural
Properties of Soft Highway Subgrade Soil Stabilized with Calcium Carbide Residue**

Ning-Jun Jiang

PhD candidate, Department of Engineering, University of Cambridge, UK. Formerly, PhD student
in Institute of Geotechnical Engineering, Southeast University, China.

Yan-Jun Du *

Professor, Institute of Geotechnical Engineering, Southeast University, Nanjing 210096, China
(*Corresponding author. PH/FAX: 86-25-83795086, E-mail: duyanjun@seu.edu.cn)

Song-Yu Liu

Professor, Institute of Geotechnical Engineering, Southeast University, Nanjing 210096, China.

Ming-Li Wei

PhD candidate, Institute of Geotechnical Engineering, Southeast University, Nanjing 210096,
China.

Suksun Horpibulsuk

Professor, School of Civil Engineering, Suranaree University of Technology, Nakhon Ratchasima
30000, Thailand.

Arul Arulrajah

Professor, Centre for Sustainable Infrastructure, Swinburne University of Technology, Victoria 3122,
Australia.

A Research Article Submitted for Possible Publication in
Canadian Geotechnical Journal

Abstract: Calcium carbide residue (CCR) is an industrial by-product, stockpiles of which are rapidly accumulating worldwide. Highway embankment construction has been identified as an avenue to consume huge quantities of CCR as an economical, less energy intensive and environmental-friendly chemical additive for soil stabilization. Previous studies have investigated the mechanical behavior of soils stabilized by CCR or blends of CCR with other additives; however, interpretation of the macro-scale geomechanical behavior of CCR stabilized soft soils from a systematically microstructural observation and analysis is relatively unknown. This paper presents a multi-scale laboratory investigation on the physical, mechanical and microstructural properties of CCR stabilized clayey soils with comparison to quicklime stabilized soils. Several series of tests were conducted to examine the Atterberg limits, particle size distribution, compaction characteristics, unconfined compressive strength, California-Bearing-Ratio and resilient modulus of the CCR stabilized clayey soils. The influences of binder content, curing time, and initial compaction state on the physical and mechanical properties of treated soils are interpreted with the aids of physicochemical and microstructural observations including soil pH, soil mineralogy obtained from X-ray diffraction and thermogravimetric analysis, and pore size distribution obtained from mercury intrusion porosimetry. Soil particle flocculation and agglomeration at the early stage and pozzolanic reactions during the entire curing time, which originate from the finer particle size, greater specific surface area and higher pH value of calcium carbide residue, are the controlling mechanisms for the superior mechanical performance of CCR stabilized soils. The outcomes of this research will contribute to the usage of CCR as a sustainable and alternative stabilizer to quicklime in highway embankment applications.

Key Words: calcium carbide residue; multi-scale; pozzolanic reaction; soil stabilization

Introduction

Calcium carbide residue (CCR) is a by-product of polyvinyl chloride (PVC), polyvinyl alcohol and acetylene production. CCR is formed through the hydrolysis of calcium carbide, as shown by the following equation ([Jaturapitakkul and Roongreung 2003](#)):

The dominant component of CCR is Ca(OH)_2 , with limited amounts of calcium carbonate (CaCO_3), SiO_2 , and trace components of sulfide, metal oxide and organic matters ([Kampala and Horpibulsuk 2013](#)). CCR is presently widespread in developing and developed countries alike ([Sharma and Reddy 2004](#); [Du et al. 2011, 2015a](#); [Horpibulsuk et al. 2013b](#); [Phetchuay et al. 2014](#)). CCR usually appears as high-alkaline and high-moisture-content slurry. If not handled properly, CCR becomes a source of pollution to surface and underground water ([Krammart and Tangtermsirikul 2004](#); [Sharma and Reddy 2004](#)). In recent years, the increasingly large production quantity of CCR due to growing demand has often resulted in serious environmental pollution with stockpile areas ([Du et al. 2011](#)). Reuse applications for CCR, particularly in large civil engineering infrastructure applications that can rapidly deplete these growing stockpiles, are urgently being sought. The usage of CCR as a sustainable cementitious binder for soil stabilization has been identified as a low-carbon and less energy intensive means to reuse this by-product and furthermore eliminate negative environmental connotations associated with stockpiling this by-product. Similar approaches have been successfully attempted in recent years for other geomaterials including geopolymer, phosphate-rich materials and demolition aggregates ([Du et al. 2011, 2014b](#); [Horpibulsuk et al. 2013b, 2014](#); [Sukmak et al. 2013a, b, 2015](#); [Arulrajah et al. 2014](#); [Cai et al. 2015](#)).

Soft clay deposits, which are widely distributed in East China regions, impose great challenges in the construction of infrastructure projects such as highway embankments ([Liu et al. 2011](#);

80 [Horpibulsuk et al. 2013b](#)). These soft clay deposits are typically of low strength, low stiffness and
81 low permeability, making them difficult to improve and compact. These difficulties often result in
82 the highway embankments having low bearing capacity and furthermore susceptible to excessive
83 settlements ([Kodikara and Chakrabarti 2005](#); [Chakrabarti and Kodikara 2007](#); [Han et al. 2007](#);
84 [Gnanendran and Piratheepan 2010](#)). Chemical stabilization is an effective method to improve the
85 engineering properties of soft clayey soils ([Shen et al. 2013](#)). Huge amount of chemical additives
86 are needed to stabilize the soft soils in-situ, given that the geometries of typical embankments are of
87 large lengths and widths. The large-scale quantities of CCR by-products generated in Eastern China,
88 creates the opportunity for the recycling of this industrial by-product in the construction of highway
89 embankment ([Du et al. 2011](#)), particularly as soft soil deposits are largely prevalent in this region.
90 The reuse of CCR in highway embankment construction is cost-economic and has no extra
91 associated embedded energy consumption compared to conventional cement-based binders, making
92 it an attracting alternative for project contractors and constructors ([Horpibulsuk et al. 2012, 2013a](#);
93 [Du et al. 2015a](#)). Similar to other chemical additives (e.g., Portland cement, fly ash and slag) for
94 soft clay stabilization ([Jin and Al-Tabbaa 2014](#); [Du et al. 2015b](#)), CCR is mixed with the parent soft
95 clayey soil and reacts with clay minerals and water to improve the strength, stiffness and durability
96 of the stabilized soil ([Kampala and Horpibulsuk 2013](#); [Du et al. 2011](#)).

97 Previous studies focused on the use of CCR alone or the blend of CCR and other chemical
98 additives in soft soils stabilization. For example, [Kampala and Horpibulsuk \(2013\)](#) examined the
99 physical and engineering properties of a problematic silty clay stabilized with CCR and stated that
100 CCR was more effective than lime in soft soil stabilization in terms of engineering, economic, and
environmental perspectives. [Horpibulsuk et al. \(2013a\)](#) investigated the strength characteristics of a
silty soil treated by the blend of CCR and fly ash and proposed a controlling strength development

101 mechanism based on different strength improvement zones. [Vichan and Rachan \(2013\)](#)
102 systematically investigated the strength development patterns of the soft Bangkok clay stabilized by
103 blends of CCR and biomass ash, and reported that the properties of both materials significantly
104 affected the strength gains. [Phetchuay et al. \(2014\)](#) used CCR- alkali activated stabilized clay
105 geopolymer as a sustainable pavement subgrade material and examined the influential factors for
106 strength development. Most of these existing studies focused on the examination of engineering
107 properties and associated influential factors affecting the strength of soils stabilized by CCR alone
108 or with blends of CCR and other additives. The interpretation of macro-scale geomechanical
109 behaviors of CCR stabilized soft soils from a systematically microstructural observation and
110 analysis is however relatively unknown. Microstructural analytical methods in geotechnical
111 engineering typically include X-ray diffraction (XRD), scanning electron microscopy (SEM),
112 mercury intrusion porosimetry (MIP) and thermogravimetric analysis (TGA) ([Mitchell and Soga](#)
113 [2005](#)). These methods have been extensively employed to produce explicit microstructural
114 supporting evidences for the hypothesis explaining geomechanical behaviors of soft soils or
115 aggregates stabilized by conventional chemical additives (e.g., Portland cement and lime) ([Locat et](#)
116 [al. 1996](#); [Al-Mukhtar et al. 2010](#); [Stoltz et al. 2012](#); [Du et al. 2014a](#); [Mohammadinia et al. 2014](#));).
117 For example, [Wild et al. \(1993\)](#) employed the XRD, SEM-EDAX and thermal analysis to
118 investigate the chemical, morphological and microstructural changes occurring during moist curing
119 and soaking of lime stabilized kaolinite. [Lemaire et al. \(2013\)](#) carried out a multi-scale studies of
120 the cement-lime stabilized plastic silty soil and interpreted the mechanical properties from the
121 physicochemical and microstructural perspective using SEM, XRD, and MIP. Similarly, multi-scale
122 observations and analysis would be helpful to understanding the controlling mechanisms of soft
123 clay stabilization by CCR.

This paper presents a multi-scale laboratory evaluation of the physical, mechanical and microstructural properties of CCR stabilized soft clayey soil. Several macro-scale series of tests were conducted to examine the Atterberg limits, particle size distribution (PSD), compaction characteristics, unconfined compressive strength (q_u), California-Bearing-Ratio (CBR) and resilient modulus (M_r) of the CCR stabilized clayey soils. Quicklime, which is used extensively in stabilizing highway subgrade materials, is selected as a control chemical additive for comparison purposes. The influences of binder content, curing time, and initial compaction state on the physical and mechanical properties of stabilized soils are interpreted with the aids of physicochemical and microstructural observations including the soil pH, soil mineralogy obtained from XRD and thermogravimetric analysis (TGA), and pore size distribution obtained from mercury intrusion porosimetry (MIP) analysis.

Materials and Methods

Soils and binders

The soil used in this study was excavated from the site of West Changzhou Ring Expressway located in Changzhou City, Jiangsu Province, China. The basic physical and engineering properties of the soil are listed in **Table 1**. The soil is classified as a low plasticity clay (CL) based on ASTM D2487 (ASTM 2011a). The result of X-ray fluorescence (XRF) analysis of the parent soil indicates that it contains 67.9% of silicon dioxide (SiO_2), 14.1% of aluminum oxide (Al_2O_3), 5% of ferric oxide (Fe_2O_3), 2.5% of magnesium oxide (MgO), and 1.3% of calcium oxide (CaO) (see **Table 2**). The particle size distribution curve of the parent soil is shown in **Fig. 1**.

CCR used in this study was collected from Jiangsu Changzhou Changfei Acetylene Manufacturing Co. Ltd. Its basic physical and chemical characteristics are listed in **Table 3** and its major chemical constituents are shown in **Table 2**. The CCR was air-dried prior to the specimen

preparation for various laboratory-scale tests due to its natural moisture content up to 60.9%. Quicklime used in this laboratory test was produced by Liyang Shanghuang Yangzhu Tianfu Lime Manufacturing Station. Basic physical and chemical characteristics of the quicklime are listed in **Table 3** and its major chemical constituents are presented in **Table 2**. This quicklime is classified as High-Calcium Lime based on ASTM C51-11 (ASTM 2011b). The particle size distribution curves of the CCR and quicklime are shown in **Fig. 1**.

Sample preparation

Prior to the series of test in this study, the standard Proctor compaction test were conducted to obtain the maximum dry density (ρ_{dmax}) and optimum water content (w_{opt}) of binder-amended soils right after mixture. For Atterberg limits and particle size distribution (PSD) tests, collected soils were air-dried before they were passed through the sieve with 0.5 mm opening size. Then, the air-dried soils were thoroughly mixed with predetermined amount of binders (i.e. CCR or quicklime) and water (approximately w_{opt}). The binder-amended soils were then cured in sealed vinyl bags at 20°C and relative humidity of 95% for 28 d before subjected to the Atterberg limits and PSD tests.

For other tests in this study, the air-dried soils were firstly prepared with predetermined amount of binders (i.e. CCR or quicklime) and water (approximately w_{opt}) in cylindrical iron molds ($\Phi 152 \times H170$ mm for CBR and M_r tests, and $\Phi 50 \times H50$ mm for unconfined compression test; soils for pH, TGA and MIP tests were sampled from the $\Phi 50 \times H50$ mm sample) via the static compaction method to achieve degree of compaction of 93%, 94% and 96%. All inner walls of molds were lubricated with Vaseline to reduce friction. All samples were subsequently cured at 20°C and relative humidity of 95% for 7 and 28 d, respectively, before testing. **Table 4** presents the binder dosage, curing time, degree of compaction, and the number of identical samples for different tests in

this study. For unconfined compression, CBR, resilient modulus, and TGA tests, three identical samples were tested. The coefficient of variation (COV) for the results of unconfined compression test, CBR and resilient modulus tests are less than 8% and COV for TGA test is less than 4%, indicating excellent repeatability of the test results.

Testing methods

Atterberg limits were conducted according to ASTM D 4318 (ASTM 2010). PSD tests for the parent soil, CCR, quicklime, and CCR and quicklime stabilized soils were conducted using a Mastersizer 2000 laser particle size analyzer (Malvern Inc., U.K.). Prior to PSD analysis, both stabilized and unstabilized soil specimens were air-dried and grinded through a 0.3 mm sieve. Then, 15 g grinded specimen was mixed with sufficient distilled water and subjected to the PSD analysis. Standard Proctor compaction test was conducted with a standard compaction effect of 600 kN-m/m³ as per ASTM D 698 (ASTM 2012). The unconfined compression test was performed based on ASTM D4219 (ASTM 2008). The rate of vertical load remained 1mm/min until the failure of the specimen. It should be noted that the specimen size in this study ($\Phi 50 \times H50$ mm) is slightly difference from the length-to-diameter ratio (2.5) recommended by ASTM D 4219. The CBR test was conducted according to ASTM D 1883 (ASTM 2014). A circular piston was used to intrude stabilized soils in a mold at a constant rate of penetration. The CBR was determined as the ratio of the unit load on the piston required to penetrate 2.5 mm or 5 mm of the test soil to the unit load required to penetrate a standard material of well-graded crushed stone. Resilient modulus test was conducted as per AASHTO T307 (AASHTO 2007), which was also previously adopted by Tastan et al. (2011). The specimen size in this study ($\Phi 152 \times H170$ mm) is modified from that in AASHTO T307 ($\Phi 102 \times H203$ mm). M_r was calculated based on the ratio of deviator stress and the

recoverable strain. Different confining and deviator stresses were applied on the specimens to cover the range of expected stresses in the field.

Physicochemical and microstructural observational tests conducted in this study include soil pH, XRD, TGA and MIP. Soil pH measurement was carried out using a HORIBA pH/COND METER D-54 as per ASTM D4972 (ASTM 2013). Both stabilized and unstabilized soils were grinded through a sieve with 2 mm opening size. The liquid to solid ratio of 1.0 was used to mix the soil and distilled water. The pH of the slurry was then measured after 1 hr of retention. In order to examine the chemical and mineralogical compositions of CCR and quicklime stabilized soils, XRD test was conducted for stabilized soils with 6% binder content at 180 d. As a reference, unstabilized soil was also subjected to the XRD test. The XRD tests were performed using a Rigaku D/Max-2500 X-ray diffractometer. Cu-K α ($\lambda = 1.540538\text{\AA}$) X-ray tube with an input voltage of 40 kV and a current of 200 mA was utilized. Prior to the test, both stabilized and unstabilized soil specimens were freeze-dried and then grinded into a sieve with 0.038 mm opening size. The tests were carried out between two-theta values of 5 to 60° with a step length of 0.02° and a scanning rate of 2°/min.

Thermogravimetric analyses (TGA) was conducted by heating a test specimen continuously from room temperature to 750°C at a heating rate of 20°C/min in a nitrogen environment. In this study, TGA was performed using a differential scanning calorimeter (Perkin-Elmer Pyris 1). After designated curing periods of 28 and 120 d, 3 identical cubic samples (1 cm $\times$ 1 cm) were extracted and soaked in absolute ethyl alcohol for 96 hr to terminate the hydration. The specimens were then dried at 30 °C and grinded through a 200-mesh sieve. Approximate 30 $\pm$ 0.5 mg sieved specimens were used for the TGA test. The results of TGA are presented as a curve of the mass loss versus temperature. The first derivative of the mass loss curve is recorded as a function of time, which is

known as derivative thermogravimetric analysis (DTG).

The MIP test is based on the fact that mercury is a non-wetting fluid that has to be pressurized in order to penetrate a porous medium (Diamond 1970). In this method, all pores are considered to be of cylindrical shape and therefore the Jurin's equation which calculates capillary pressure can be applied in MIP method:

$$(2) \quad d = - \frac{4\tau \cos \theta}{p}$$

where d is the diameter of the pore intruded, τ is the surface tension of intruded liquid (i.e. mercury), θ is the contact angle, and p is the applied pressure. In this study, MIP test was carried out using an AutoPore IV 9510 mercury intrusion porosimeter (Micromeritics Co. Ltd. USA). The maximum applied pressure is 6×10^4 psi (i.e. 413 MPa) and the surface tension of mercury is 4.84×10^{-4} N/mm at 25°C (Mitchell and Soga 2005). The contact angle is taken as 135°. After curing periods, stabilized soil specimens were broken up to about 1 cm × 1 cm cubes in a careful manner to eliminate disturbance. Liquid nitrogen was used to freeze the soil specimens, after which the specimens were placed in a freezing unit with a vacuum chamber, and were dried by sublimation of the frozen water at a temperature of -80 °C. (Penumadu and Dean 2000; Li and Zhang 2009).

Results and Analysis

Atterberg limits

The results of Atterberg limits tests are shown in Table 5. It is found that both liquid limit (w_L) and plastic limit (w_p) of CCR and quicklime stabilized soils are higher than those of unstabilized soils, regardless of binder dosage. In contrast, plastic index ($I_p = w_L - w_p$) values of both CCR and quicklime stabilized soils decrease by approximate 15% as compared to those of unstabilized soils. Kinuthia (1999) and Du et al. (2014a) indicated that formations of flocculate and agglomerate

(short-term), and pozzolanic reactions (long-term) in lime stabilized soils were able to remarkably modify w_L and w_p . Due to the similarity in chemical components between CCR and quicklime, the mechanism proposed by Kinuthia (1999) can explain the variations of Atterberg limits of both CCR and quicklime stabilized soil with binder content and curing time in this study. The decrease in I_p values with amendment of CCR or quicklime observed in this study is consistent with those examined by previous studies (Locat et al. 1996; Du et al. 1999) which found that the addition of chemical additives (such as lime) could result in an increase in both w_L and w_p but a reduction in I_p .

Particle size distribution (PSD)

The results of PSD test is shown in **Table 6**. After 28 d curing time, the addition of 4% and 6% CCR leads to reduction of clay-sized particle percentage from 13.6% to 7.0% and to 3.8%, respectively, which are higher than the cases of quicklime addition (from 13.6% to 10.0% and to 8.2%, respectively). The sand-sized particle percentage of CCR and quicklime stabilized soils increase substantially from 2.5% to 37.8% and to 60.7 for 4% and 6% CCR, as well as from 2.5% to 26.4% and to 26.7% for 4% and 6% quicklime, respectively. The changes in clay- and sand-sized particle percentages in the stabilized soils are dominantly attributed to both short-term flocculation formation and long-term pozzolanic reactions (Nalbantoglu and Tuncer 2001; Tran et al. 2014). The flocculation contributes to agglomeration of fine particles (Nalbantoglu and Tuncer 2001; Kampala et al. 2013) and the synthesized pozzolanic products would coat the surface of soil particles (Tran et al. 2014), both making relatively high fraction of coarse-grained particles.

In comparison with quicklime, CCR stabilized soils exhibit 143% to 228% higher sand-sized particle percentage after curing for 28 d. The clay-sized particle percentages of CCR stabilized soils are 29% to 54% less than quicklime stabilized soils at 28 d, respectively. The observations suggest

that CCR yields a superior capability for modifying particle size distribution of the soils as compared to the quicklime.

Compaction characteristics

The results of standard compaction test show that when the binder content increases from 4 to 6%, w_{op} slightly changes from 13.4 to 14.1% for CCR and from 13.2 to 13.4% for quicklime, respectively. In contrast, ρ_{dmax} reduces from 1.78 to 1.74 g/cm³ and from 1.73 to 1.70 g/cm³ for CCR and quicklime stabilized soils, respectively, as a consequence of increase in the binder content from 4 to 6%. The phenomena are consistent with those reported by Fahoum et al. (1996), who also observed the reduction of ρ_{dmax} with increasing lime content for cohesive soils, and Kampala and Horpibulsuk (2013), who reported the reduction of ρ_{dmax} with increasing CCR content for silty clay. The reason of the phenomena is predominantly attributed to the flocculation and agglomeration, as a consequence of cation exchange, resulting in material bulking (Kinuthia et al. 1999). The ρ_{dmax} values of the CCR stabilized soil are always higher than those of quicklime stabilized soils at the binder contents of 4 and 6%, indicating that CCR stabilized soil can achieve a better compaction performance relative to the quicklime with the same dosage.

Unconfined compressive strength

Figure 2 shows the effects of curing time, degree of compaction and binder content on the q_u of CCR and quicklime stabilized soils. The q_u of unstabilized soils is also marked in **Fig. 2** for comparison. It can be noticed that q_u keeps increasing steadily with curing time, irrespective of the degree of compaction and binder content for both stabilized soils. More specifically, the CCR stabilized soil exhibits notable strength development at the initial 60 d than the subsequent 60 d,

regardless of the degree of compaction. However, the quicklime stabilized soil gains predominant strength at the initial 30 d with 94 and 96% degree of compaction. With 93% degree of compaction, the predominant strength development occurs at the initial 60 d. Moreover, it is evident that higher content of CCR or quicklime results in higher q_u values for all the curing times tested. At the same binder content, the q_u values of CCR stabilized soil are higher than those of the quicklime stabilized soil regardless of the curing time and degree of compaction. The strength development for CCR and quicklime stabilized soft clayey soils in this study is consistent with that reported by [Kampala and Horpibulsuk \(2013\)](#). The strength growth at early stage is attributable to the flocculation and agglomeration of the soil particles ([Kinuthia et al. 1999](#)) while the long-term strength development is determined by the pozzolanic reactions ([Wild et al., 1993](#)).

CCR and quicklime stabilized soils have a discrepancy in the effect of degree of compaction on the strength development. The q_u values at 120 d for CCR stabilized soils are around 2250 kPa regardless of the degree of compaction. In contrast, dependence of q_u on the initial compaction state is noticeable for quicklime stabilized soils cured for 120 d. For example, in the case of 6% amendment, the q_u values at 120 d are 1600 and 2200 kPa for 93% and 96% degree of compaction, respectively. [Le Runigo et al. \(2009\)](#) stated that the impact of compaction energy on the pore size distribution of quicklime stabilized silty soil is margin, indicating a similar soil fabric even under different degree of compaction conditions. However, [Osinubi \(1998\)](#) showed that higher compaction energy was related to higher q_u values for lime stabilized soils, which is consistent with the results of quicklime stabilized soil tested in this study. Since the binder contents adopted in this study are not higher than 6%, the CCR stabilized soils are in the active zone, as suggested by [Horpibulsuk et al. \(2013\)](#). In contrast, the quicklime stabilized soils are in the inert or deterioration zone as suggested by [Bell \(1996\)](#). In the active zone, the long-term q_u of the CCR stabilized soil

increases with increasing binder content, which is due to the fact that all input portlandite is consumed through pozzolanic reactions (Horpibulsuk et al. 2013). However, in the inert or deterioration zone, the q_u of the quicklime stabilized soil ceases to increase or decrease with increasing binder content, which is caused by internal-structure damage due to presence of excessive free lime (Horpibulsuk et al. 2013). Therefore, when the stabilized soils are in different zones (i.e., active zone and inert or deterioration zone), the effect of degree of compaction on their q_u would be different. This may explain the discrepancy between CCR and stabilized soils in terms of the effect of degree of compaction on the q_u .

California Bearing Ratio (CBR)

Figure 3 presents the effects of curing time, binder content on CBR values with various degree of compaction. The CBR values of both CCR and quicklime stabilized soils are dramatically higher than that of the unstabilized soil, and they increase steadily with increasing curing time, due to the flocculation and agglomeration of soil particles at early stage and pozzolanic reactions at long term (Kinuthia et al. 1999). The CBR values of both CCR and quicklime stabilized soils increase with increasing degree of compaction, which is consistent with that reported by Osinubi (1998). In contrast, the binder content affects CBR values in a different manner for CCR and quicklime stabilized soils. The CBR values of CCR stabilized soils at two binder contents (4 and 6%) are practically the same, while the quicklime stabilized soil exhibits approximate 30% increase in the CBR when the binder content increases from 4% to 6%.

Similar to the unconfined compression test results, the CCR stabilized soils possess much higher CBR values relative to the quicklime stabilized soils, regardless of the binder content, curing time and degree of compaction within the considered range. This result is consistent with that

obtained from the full-scale field trial tests (Du et al. 2015a), confirming that the CCR stabilization brings higher bearing capacity for the highway soft clayey soils relative to the quicklime. In addition, the measured CBR values also satisfies the requirement specified by the China highway construction standard ($\text{CBR} \geq 8\%$) (China MOT 2004).

Resilient modulus (M_r)

Figure 4 illustrates the development of M_r for CCR and quicklime stabilized soils with curing time and degree of compaction. It is evident that CCR and quicklime stabilization leads to a significant increase in M_r , as compared to the unstabilized soil. The M_r values of both CCR and quicklime stabilized soils at 28 d are approximately two times those at 7 d. Elevation of degree of compaction from 94% to 96% results in approximate 20% increase in M_r for the CCR stabilized soil, whereas only marginal increase in M_r for the quicklime stabilized soil. The change of M_r with curing time and degree of compaction is similar to that of q_u (see **Fig. 2**) and CBR (see **Fig. 3**).

The M_r values of the CCR stabilized soils are found to be remarkably larger than those of quicklime stabilized soils. At 7 d, the M_r values of CCR stabilized soils with degree of compaction of 94% and 96% are 15% and 29%, respectively, higher than those of quicklime stabilized soils. This difference increases to 31% and 44% at 28 d for the degrees of compaction of 94% and 96%, respectively.

Soil pH

Figure 5 shows the changes in measured soil pH values of CCR and quicklime stabilized soils with the curing time. It is found that pH values of both CCR and quicklime stabilized soils decrease gradually with increasing curing time, which is attributed to the pozzolanic reactions between

portlandite ($\text{Ca}(\text{OH})_2$) and reactive $\text{SiO}_2/\text{Al}_2\text{O}_3$ in the soil matrix expressed by the following equation (Kinuthia et al. 1999):

During the pozzolanic reactions, alkaline portlandite is gradually consumed and transformed to less alkaline secondary cementitious products (e.g., C-S-H and C-A-S-H), leading to reduction in soil pH (Kinuthia et al. 1999; Al-Mukhtar et al. 2010; Du et al. 2014a). It is noted that when pH of stabilized soils is higher than 10 to 11, the reactive $\text{SiO}_2/\text{Al}_2\text{O}_3$ in soil matrix would keep dissolving (Saride et al. 2010) while the formed secondary cementitious products are still thermodynamically stable (Stronach and Glasser 1997). Moreover, the pH of the CCR stabilized soil is higher than that of the quicklime stabilized one during the entire curing period. This is mainly due to the higher pH of CCR (12.84) than that of quicklime (12.74), as shown in Table 3.

X-Ray diffraction (XRD)

Figure 6 presents the XRD diffractograms of the stabilized and unstabilized soils. The minerals in the unstabilized soil are predominantly quartz, kaolinite and illite with trace montmorillonite. For the CCR stabilized soil, formation of C-S-H is detected at 2θ of 27.5° , 28.3° , 52.9° and 54.5° , respectively. In contrast, no distinct peaks for portlandite are identified in the CCR stabilized soil. As C-S-H is the secondary cementitious products (see Eqs. (3) and (4)) formed in the pozzolanic reactions, the identified peaks of C-S-H and absence of portlandite in the CCR stabilized soil at 180 d confirms the completed progress of pozzolanic reactions. The XRD diffractogram of the quicklime stabilized soil reveals the formation of both C-S-H (27.5° and 52.9°) and calcite (13.1° , 29.4° and 36.0°). The formation of calcite is attributed to the air exposure of soil during the curing

period and subsequent carbonation of quicklime and hydrated products (Verbrugge et al. 2011). The vulnerability of the quicklime stabilized soil to the carbonation, as compared to the CCR stabilized soil, primarily occurs at the early stage (Hunter 1988; Al-Mukhtar et al. 2012), during which quicklime stabilized soils develop relatively high porosity (which is demonstrated from the MIP test presented in the later section) and hence relatively large exposure area to carbon dioxide (CO₂) in the air.

Thermogravimetric analysis

Figure 7 shows the TGA and DTG results for the CCR and quicklime stabilized soils with 6% content at 28 and 180 d. The results of TGA are presented as a curve of the mass loss/first derivative of the mass loss versus temperature. Significant mass losses can be observed at a temperature of 50 to 200 °C and 200 to 300 °C from peaks in the DTG curves. The peaks in DTG curves (or mass losses in TGA curves) correspond to the presence of pozzolanic reaction products (C-S-H, C-A-H and C-A-S-H) during their thermal decompositions (HaHa et al. 2011). In addition, a sharp peak can be identified at the temperature of 425 °C, which is confirmed to be portlandite (HaHa et al. 2011). Since the pozzolanic reaction products (*viz.* C-S-H, C-A-H and C-A-S-H) have relatively low degree of crystallinity, their contents could not be calculated by the stoichiometric relation. In this study, the loss of hygroscopic water corresponding to the temperature of 50 to 200 °C and 200 to 300 °C was arbitrarily used to represent the content of C-S-H, and summed content of C-A-H and C-A-S-H, respectively. **Table 7** shows the content of C-S-H and summed content of C-A-H and C-A-S-H in the soils tested. As seen in **Table 7**, the content of C-S-H and summed content of C-A-H and C-A-S-H increase with the increase in curing time. At both 28 and 120 d, the content of C-S-H (1.861% and 2.108% for 28 and 120 d, respectively) and summed content of C-A-H and

C-A-S-H in the CCR stabilized soil (0.95% and 1.01% for 28 and 120 d, respectively) are higher than those in the quicklime stabilized soil (1.804% and 1.98% (C-S-H), 0.86% and 0.864% (sum of C-A-H and C-A-S-H) for 28 and 120 d, respectively). **Figure 8** illustrates the correlations between q_u and summed content of C-S-H, C-A-H and C-A-S-H of the soils with 6% binder content. It is evident that higher summed content of C-S-H, C-A-H and C-A-S-H corresponds to higher q_u of the soils.

Mercury intrusion porosimetry (MIP)

Figure 9 presents the MIP results for the CCR and quicklime stabilized soils with 6% binder content, which are illustrated by the relations between cumulative pore volume and pore size. It is found that the total pore volumes decrease steadily with elapsed curing time for both CCR and quicklime stabilized soils. When the curing time increases from 28 d to 60 d, the reductions of total pore volumes are 0.03 mL/g and 0.08 mL/g for CCR and quicklime stabilized samples, respectively. The total pore volume for both CCR and quicklime stabilized soils, however, changes marginally from 60 d to 120 d. Therefore, pore-filling by the pozzolanic products occurs primarily at the initial 60 d curing.

The CCR stabilized soil has a significantly smaller cumulative pore volume in all ranges of measured pore sizes (**Fig. 9**). Particularly, the total pore volume of the CCR stabilized soil is approximately 0.054 mL/g lower than that of quicklime (0.23 mL/g) at 28 d. Nevertheless, the total pore volume is almost identical for both soils at 60 d. At 120 d curing, the pore size distribution curves of both stabilized soils are well overlapped, indicating they have similar long-term porosimetry characteristics.

Figure 10 shows the pore volumes of different types of pores in the CCR and quicklime

stabilized soils at different curing time. [Horpibulsuk et al. \(2009\)](#) reported that for the cement and fly-ash stabilized silty clays, pore diameters of 0.01 and 10 μm are thresholds between intra-aggregate and inter-aggregate pores, and inter-aggregate and large air pores, respectively. It is found that the volumetric reduction in the large air pores with curing time, primarily, contributes to the reduction in the total pore volume for CCR and quicklime stabilized soils. The quicklime stabilized soil possesses greater volume of large air pores relative to the CCR stabilized soil regardless of the curing time. This coincides with the higher q_u value of the CCR stabilized soil over the quicklime stabilized soil. Previous studies also reported the similar relation between strength and volume of large pores in the soils. For example, [Munkholm et al. \(2002\)](#) found that tensile strength was conversely linearly correlated to the volume of pores with diameter $> 30 \mu\text{m}$ for sandy loam. [Locat et al. \(1996\)](#) found that the mechanical properties of lime stabilized inorganic clay were mainly controlled by the volume of pores with diameter $> 0.01 \mu\text{m}$.

Discussion

The results of this laboratory evaluation study demonstrate that the CCR stabilized clayey soil has superior mechanical performances than the quicklime stabilized soil. This advantage in mechanical performance can be interpreted from the physicochemical and microstructural points of view. At the early stage of curing, the binder-soil interaction is dominated by cation exchange ([Hunter 1988](#)). The cation exchange between the calcium ions from the hydration of CCR or quicklime and the readily exchangeable cations initially adsorbed on the clay particle results in a reduced thickness of diffusion double layer of clay particles, and formation of flocculation and agglomeration of soil particles as a consequence ([Kinuthia et al. 1999](#); [Saride et al. 2010](#)). Finer particle size and larger specific surface area of the binder particles are preferable for the formation

of flocculation and agglomeration (Kinuthia et al. 1999). Since the CCR has higher amount of fine particles and greater specific surface area relative to the quicklime (Table 3), flocculation and agglomeration of soil particles would be more notable in the CCR stabilized soil. This mechanism is substantiated by the analysis of particle size distribution of the stabilized soils, in which the particle size of the CCR stabilized soil is coarser than that of the quicklime stabilized soil at 28 d (Table 6).

The long-term interaction between the CCR or quicklime and soil is dominated by pozzolanic reactions (Hunter 1988). Portlandite reacts with the reactive $\text{SiO}_2/\text{Al}_2\text{O}_3$ in soil matrix and produces pozzolanic products including C-S-H, C-A-H and C-A-S-H (Kinuthia et al. 1999; Al-Mukhtar et al. 2010). Finer particle size and larger specific surface area of the binder particle are more preferable for the implementation of reactions between portlandite and reactive $\text{SiO}_2/\text{Al}_2\text{O}_3$ in the soil matrix. Therefore, higher amount of pozzolanic products is found to form in the CCR stabilize soil relative to the quicklime stabilized soil at the same curing time (Table 7).

The pH of the raw binder material also contributes to the different mechanical performances of the stabilized soils, since the pozzolanic reactions are controlled by the pH of binder–soil system and higher alkaline environment facilitates the dissolution of reactive $\text{SiO}_2/\text{Al}_2\text{O}_3$ within clay minerals (Stronach and Glasser 1997; Saride et al. 2010). As the pH values of the CCR stabilized soil are higher than those of the quicklime stabilized soil (Fig. 5), the amendment of CCR to the parent soil would generate a faster dissolution rate of reactive $\text{SiO}_2/\text{Al}_2\text{O}_3$ in the soil matrix and rate of pozzolanic reactions as a consequence. Because of the essential role of pozzolanic products in soil pore filling, soil particle bonding and soil strength development, a superior mechanical performance of the CCR stabilized soil over the quicklime stabilized soil is expected (Figs. 2 to 4).

In summary, it can be postulated that the variation in the physical and mechanical properties (Atterberg limits, particle size distribution, compaction characteristics, q_u , CBR, and M_r) of the

CCR stabilized soil could be identified by resorting to systematic investigations to detect changes in the physicochemical and microstructural characteristics via soil pH, XRD, TGA and MIP analyses. The superior mechanical performances for the CCR stabilized soil can be explained fundamentally from the basic properties of the binders and soil-binder interactions (flocculation/agglomeration and pozzolanic reactions). Furthermore, environmental impacts of the use of CCR in soil stabilization including leachability of heavy metals have been evaluated using batch-type leaching tests; the results demonstrated that CCR is an environmental-friendly binder (Du et al. 2015a). Further study is recommended for CCR stabilization of soils with entirely different properties (e.g., silty and sandy soils).

Conclusions

This study presents a multi-scale laboratory investigation of physical, mechanical and microstructural properties of CCR stabilized highway soft clayey soils, with a comparison with quicklime stabilized soils. The following conclusions can be drawn from this research:

- (1) The stabilization by CCR or quicklime results in increase in the liquid limit and plastic limit while decrease in the plasticity index. The addition of CCR or quicklime also leads to an increase in sand-sized particle percentage. Under the same curing period and binder content, the CCR stabilized soil attains higher sandy-sized particle percentage relative to the quicklime stabilized soil. The increase in the curing time and binder content facilitates larger q_u , CBR and M_r . Under the same curing period, binder content and degree of compaction, the CCR stabilized soil exhibits superior mechanical performances relative to the quicklime stabilized soil.

- (2) Both CCR and quicklime stabilized soils display a gradual reduction in soil pH with

increased curing time, and pH of the CCR stabilized soil is always higher relative to the quicklime stabilized soil. Pozzolanic products like C-S-H, C-A-H and C-A-S-H are identified in both CCR and quicklime stabilized soils. The summed content of pozzolanic products in the CCR stabilized soil is higher than that in the quicklime stabilized soil. The CCR stabilized soil has a much smaller total pore volume than the quicklime stabilized soil within the initial 28 d, though the difference is almost eliminated at 120 d. The strength of the stabilized soil is found conversely correlated with the large pore volume in the soil.

(3) The fundamental mechanisms for the superior mechanical performances of the CCR stabilized soil over quicklime stabilized soil are the faster and more complete formation of flocculation and agglomeration of soil particles at the early stage as well as pozzolanic reactions within soils for the entire curing time. Finer particle size, greater specific area and higher pH value of CCR than quicklime are the essential contributors to the controlling mechanisms.

Acknowledgements

Financial support for this research was obtained from the National Natural Science Foundation of China (Grant No. 51278100, 41330641 and 41472258) and Natural Science Foundation of Jiangsu Province (Grant No. BK2012022). The fifth author is grateful to the Thailand Research Fund under the TRF Senior Research Scholar program Grant No. RTA5680002.

References

AASHTO 2007. Standard method of test for determining the resilient modulus of soils and aggregate materials. AASHTO T307-99, *American Association of State Highway and*

- 516 *Transportation Officials*, Washington D.C., USA.
- 517 Al-Mukhtar, M., Lasledj, A., Alcover, J.F. 2010. Behaviour and mineralogy changes in lime-treated
518 expansive soil at 20 °C. *Applied Clay Science*, **50** (2): 191-198. doi:10.1016/j.clay.2010.07.023
- 519 Al-Mukhtar, M., Khattab, S., and Alcover, J.F. 2012. Microstructure and geotechnical properties of
520 lime-treated expansive clayey soil. *Engineering Geology*, **139-140**: 17-27.
521 doi:10.1016/j.enggeo.2012.04.004
- 522 Arulrajah, A., Disfani, M., Horpibulsuk, S., Suksiripattanapong, C. and Prongmanee, N. 2014.
523 Physical properties and shear strength responses of recycled construction and demolition
524 materials in unbound pavement base/subbase applications. *Construction and Building Materials*.
525 **58**: 245–257. doi:10.1016/j.conbuildmat.2014.02.025
- 526 ASTM 2008. Standard test method for unconfined compressive strength index of chemical- grouted
527 soils. ASTM D4219-08, *American Society for Testing and Materials*, West Conshohocken,
528 USA.
- 529 ASTM 2010. Standard test methods for liquid limit, plastic limit, and plasticity index of soils.
530 ASTM D4318-10, *American Society for Testing and Materials*, West Conshohocken, USA.
- 531 ASTM 2011a. Standard practice for classification of soils for engineering purposes (unified soil
532 classification system). ASTM D2487-11, *American Society for Testing and Materials*, West
533 Conshohocken, USA.
- 534 ASTM 2011b. Standard terminology relating to lime and limestone (as used by the industry).
535 ASTM C51-11, *American Society for Testing and Materials*, West Conshohocken, USA.
- 536 ASTM 2012. Standard test methods for laboratory compaction characteristics of soil using standard
537 effort (12 400 ft-lbf/ft³ (600 kN-m/m³)). ASTM D698-12, *American Society for Testing and*

- 538 *Material*, West Conshohocken, USA.
- 539 ASTM 2013. Standard test method for pH of soils. ASTM D4972-13, *American Society for Testing*
540 *and Material*, West Conshohocken, USA.
- 541 ASTM 2014. Standard test method for California Bearing Ratio (CBR) of laboratory-compacted
542 soils. ASTM D1883-14, *American Society for Testing and Material*, West Conshohocken, USA.
- 543 Bell, F.G. 1996. Lime stabilization of clay minerals and soils. *Engineering Geology*, **42**(4): 223-237.
544 doi:10.1016/0013-7952(96)00028-2
- 545 Cai, G.H., Du, Y.J., Liu, S.Y., Singh, D.N. 2015. Physical properties, electrical resistivity and
546 strength characteristics of carbonated silty soil admixed with reactive magnesia. *Canadian*
547 *Geotechnical Journal*. doi: 10.1139/cgj-2015-0053
- 548 Chakrabarti, S. and Kodikara, J.K. 2007. Direct tensile failure of cementitiously stabilised crushed
549 rock materials. *Canadian Geotechnical Journal*, **44**(2): 231-240. doi: 10.1139/t06-102
- 550 China MOT. 2004. Specifications for Design of Highway Subgrades. *China Ministry of*
551 *Transportation*, JTG D30-2004, Beijing, China.
- 552 Diamond, S. 1970. Pore size distributions in clays. *Clays and Clay Minerals.*, **18**: 7-23.
- 553 Du, Y.J., Li, S.L., and Hayashi, S. 1999. Swelling–shrinkage properties and soil improvement of
554 compacted expansive soil, Ning-Liang Highway, China. *Engineering Geology*, **53**(3-4):
555 351-358. doi: 10.1016/S0013-7952(98)00086-6
- 556 Du, Y.J., Zhang, Y.Y., Liu, S.Y. 2011. Investigation of strength and california bearing ratio
557 properties of natural soils treated by calcium carbide residues. *In Proceedings of Geo-Frontiers*
558 2011: Advances in Geotechnical Engineering, Dallas, Texas, 13-16 March 2011. American
559 Society of Civil Engineers, Reston, USA, pp. 1237-1244.

- 560 Du, Y.J., Jiang, N.J., Liu, S.Y., Jin, F., Singh, D.N., and Puppala, A.J. 2014a. Engineering properties
561 and microstructural characteristics of cement stabilized zinc-contaminated kaolin. Canadian
562 Geotechnical Journal, **51**(3), 289-302. doi: 10.1139/cgj-2013-0177
- 563 Du, Y.J., Wei, M.L., Reddy, K.R., Jin, F., Wu H.L., and Liu, Z.P. 2014b. New phosphate-based
564 binder for stabilization of soils contaminated with heavy metals: Leaching, strength and
565 microstructure characterization. Journal of Environmental Management, **146**: 179-188. doi:
566 doi:10.1016/j.jenvman.2014.07.035
- 567 Du, Y.J., Jiang, N.J., Liu, S.Y., Horpibulsuk, S., and Arulrajah, A. 2015a. Full-scale field trial
568 evaluating the performance of highway subgrade soil stabilized with calcium carbide residue.
569 Soils and Foundations, under review.
- 570 Du, Y.J., Bo, Y.L., Jin, F., and Liu, C.Y. 2015b. Durability of reactive magnesia-activated
571 slag-stabilized low plasticity clay subjected to drying–wetting cycle. European Journal of
572 Environmental and Civil Engineering. doi: 10.1080/19648189.2015.1030088
- 573 Fahoum, K., Aggour, M.S., and Amini, F. 1996. Dynamic properties of cohesive soils treated with
574 lime. Journal of Geotechnical Engineering, **122**(5): 382-389. doi:
575 10.1061/(ASCE)0733-9410(1996)122:5(382)
- 576 Gnanendran, C.T., Piratheepan, J. 2010. Determination of fatigue life of a granular base material
577 lightly stabilized with slag lime from indirect diametral tensile testing. Journal of
578 Transportation Engineering, **136**(8): 736-745. doi: 10.1061/(ASCE)TE.1943-5436.0000138
- 579 HaHa, M.B., Lothenbach, B., Saout, G.L., Winnefeld, F. 2011. Influence of slag chemistry on the
580 hydration of alkali-activated blast-furnace slag - Part I: Effect of MgO. Cement and Concrete
581 Research, **41**(9): 955-963. doi:10.1016/j.cemconres.2011.05.002

- 582 Han, J., Oztoprak, S., Parsons, R.L., and Huang, J. 2007. Numerical analysis of foundation columns
583 to support widening of embankments. *Computers and Geotechnics*, **34**(6): 435-448.
584 doi:10.1016/j.compgeo.2007.01.006
- 585 Horpibulsuk, S., Rachan, R., Raksachon, Y. 2009. Role of fly ash on strength and microstructure
586 development in blended cement stabilized silty clay. *Soils and Foundations*, **49**(1): 85-98.
- 587 Horpibulsuk, S., Phetchuay, C., and Chinkulkijniwat, A. 2012. Soil stabilization by calcium carbide
588 residue and fly ash. *Journal of Materials in Civil Engineering*, **24**(2): 184–193. doi:
589 10.1061/(ASCE)MT.1943-5533.0000370
- 590 Horpibulsuk, S., Phetchuay, C., Chinkulkijniwat, A., Cholphatsorn, A. 2013a. Strength
591 development in silty clay stabilized with calcium carbide residue and fly ash. *Soils and*
592 *Foundations*, **53**(4): 477-486. doi:10.1016/j.sandf.2013.06.001
- 593 Horpibulsuk, S., Chinkulkijniwat, A., and Shen, S.L. 2013b. Engineering properties of recycled
594 calcium carbide residue stabilized clay as fill and pavement materials. *Construction and*
595 *Building Materials*, **46**: 203-210. doi:10.1016/j.conbuildmat.2013.04.037
- 596 Hunter, D. 1988. Lime-induced heave in sulfate-bearing clay soils. *Journal of Geotechnical*
597 *Engineering*, **114**(2): 150-167. doi: 10.1061/(ASCE)0733-9410(1988)114:2(150)
- 598 Jaturapitakkul, C. and Roongreung, B. 2003. Cementing material from calcium carbide residue-rice
599 husk ash. *Journal of Materials in Civil Engineering*, **15**(5): 470–475. doi:
600 10.1061/(ASCE)0899-1561(2003)15:5(470)
- 601 Jin, F and Al-Tabbaa, A. 2014. Evaluation of novel reactive MgO activated slag binder for the
602 immobilisation of lead and zinc. *Chemosphere*, **117**: 285-294.
603 doi:10.1016/j.chemosphere.2014.07.027

- 604 Kinuthia, J.M, Wild, S., Jones, G.I. 1999. Effects of monovalent and divalent metal sulphates on
605 consistency and compaction of lime-stabilised kaolinite. *Applied Clay Science*, **14** (1-3): 27-45.
606 doi:10.1016/S0169-1317(98)00046-5
- 607 Kodikara, J.K. and Chakrabarti, S. 2005. Modelling of moisture loss in cementitiously stabilised
608 pavement materials. *International Journal of Geomechanics*, **5**(4): 295-303. doi:
609 10.1061/(ASCE)1532-3641(2005)5:4(295)
- 610 Krammart, P., Tangtermsirikul, S. 2004. Properties of cement made by partially replacing cement
611 raw materials with municipal solid waste ashes and calcium carbide waste. *Construction and*
612 *Building Materials*, **18**(8): 579-583. doi:10.1016/j.conbuildmat.2004.04.014
- 613 Kampala, A. and Horpibulsuk, S. 2013. Engineering properties of silty clay stabilized with calcium
614 carbide residue. *Journal of Materials in Civil Engineering*, **25**(5): 632-644. doi:
615 10.1061/(ASCE)MT.1943-5533.0000618
- 616 Kampala, A., Horpibulsuk, S., Chinkulkijniwat, A. and Shen, S.L. 2013. Engineering properties of
617 recycled calcium carbide residue stabilized clay as fill and pavement materials. *Construction*
618 *and Building Materials*, **46**: 203-210. doi:10.1016/j.conbuildmat.2013.04.037
- 619 Lemaire K., Deneele, D., Bonnet, S., and Legret, M. 2013. Effects of lime and cement treatment on
620 the physicochemical, microstructural and mechanical characteristics of a plastic silt.
621 *Engineering Geology*, **166**: 255-261. doi:10.1016/j.enggeo.2013.09.012
- 622 Le Runigo, B., Cuisinier, O., Cui, Y.-J., Ferber, V., Deneele, D. 2009. Impact of initial state on the
623 fabric and permeability of a lime-treated silt under long-term leaching. *Canadian Geotechnical*
624 *Journal*, **46** (11): 1243-1257. doi: 10.1139/T09-061
- 625 Liu, S.Y., Shao, G.H., Du, Y.J., and Cai, G.J. 2011. Depositional and geotechnical properties of

- 626 marine clays in Lianyungang, China. *Engineering Geology*, **121**(1-2): 66-74.
627 doi:10.1016/j.enggeo.2011.04.014
- 628 Li, X., and Zhang, L.M. 2009. Characterization of dual-structure pore-size distribution of soil.
629 *Canadian Geotechnical Journal*, **46**(2): 129-141. doi: 10.1139/T08-110
- 630 Locat, J., Tremblay, H., Leroueil, S. 1996. Mechanical and hydraulic behavior of a soft inorganic
631 clay treated with lime. *Canadian Geotechnical Journal*, **33**(4): 654-669. doi:
632 10.1139/t96-090-311
- 633 Mitchell, J.K, and Soga, K. 2005. *Fundamentals of soil behavior*, John Wiley & Sons, Hoboken,
634 USA.
- 635 Mohammadinia, A., Arulrajah, A., Sanjayan, J., Disfani, M.M., Bo, M.W. and Darmawan, S. 2014.
636 Laboratory evaluation of the use of cement-treated construction and demolition materials in
637 pavement base/subbase applications. *Journal of Materials in Civil Engineering*, 04014186. doi:
638 10.1061/(ASCE)MT.1943-5533.0001148
- 639 Munkholm, L.J., Schjønning, P., and Kay, B.D. 2002. Tensile strength of soil cores in relation to
640 aggregate strength, soil fragmentation and pore characteristics. *Soil & Tillage Research*, **64**,
641 125-135. doi:10.1016/S0167-1987(01)00250-1
- 642 Nalbantoglu, Z., and Tuncer, E.R. 2001. Compressibility and hydraulic conductivity of a chemically
643 treated expansive clay. *Canadian Geotechnical Journal*, **38**(1): 154-160. doi: 10.1139/t00-076
- 644 Osinubi, K. 1998. Influence of compactive efforts and compaction delays on lime-treated soil.
645 *Journal of Transportation Engineering*, **124**(2): 149–155. doi:
646 10.1061/(ASCE)0733-947X(1998)124:2(149)
- 647 Penumadu, D., and Dean, J. 2000. Compressibility effect in evaluating the pore-size distribution of

- 648 kaolin clay using mercury intrusion porosimetry. Canadian Geotechnical Journal, **37**(2):
649 393-405. doi: 10.1139/t99-121
- 650 Phetchuay, C., Horpibulsuk, S., Suksiripattanapong, C., Chinkulkijniwat, A., Arulrajah, A., and
651 Disfani, M.M. 2014. Calcium carbide residue: Alkaline activator for clay–fly ash geopolymer.
652 Construction and Building Materials, **69**: 285-294. doi:10.1016/j.conbuildmat.2014.07.018
- 653 Saride, S., Puppala, A.J., and Chikyala, S.R. 2010. Swell-shrink and strength behaviors of lime and
654 cement stabilized expansive organic clays. Applied Clay Science, **85**: 155-164.
655 doi:10.1016/j.clay.2013.09.008
- 656 Sharma, H.D., Reddy, K.R., 2004. *Geoenvironmental engineering: site remediation, waste*
657 *containment, and emerging waste management technologies*. John Wiley & Sons, Inc, Hoboken,
658 New Jersey.
- 659 Shen, S.L., Wang, Z., Yang, J., and Ho, C. 2013. Generalized approach for prediction of jet grout
660 column diameter. Journal of Geotechnical and Geoenvironmental Engineering, **139**(12):
661 2060–2069. doi:10.1061/(ASCE)GT.1943-5606.0000932
- 662 Stoltz, G., Cuisinier, O., and Masrouri, F. 2012. Multi-scale analysis of the swelling and shrinkage
663 of a lime-treated expansive clayey soil. Applied Clay Science, **61**: 44-51.
664 doi:10.1016/j.clay.2012.04.001
- 665 Stronach, S.A., and Glasser, F.P. 1997. Modelling the impact of abundant geochemical components
666 on phase stability and solubility of the CaO-SiO₂-H₂O system at 25°C: Na⁺, K⁺, SO₄²⁻, Cl⁻ and
667 CO₃²⁻. Advances in Cement Research, **9**(36): 167–181. doi:10.1680/adcr.1997.9.36.167
- 668 Sukmak, P., Horpibulsuk, S. and Shen, S.L. 2013a. Strength development in clay-fly ash
669 geopolymer. Construction and Building Materials, **40**: 566-574. doi:

10.1016/j.conbuildmat.2012.11.015

Sukmak, P., Horpibulsuk, S., Shen, S.L., Chindaprasirt, P., and Suksiripattanpong, C. 2013b.

Factors influencing strength development in clay-fly ash geopolymer. *Construction and*

Building Materials, **47**: 1125-1136. doi:10.1016/j.conbuildmat.2013.05.104

Sukmak, P., Silva, P.D., Horpibulsuk, S. and Chindaprasirt, P. 2015. Sulfate resistance of

clay-Portland cement and clay-high calcium fly ash geopolymer. *Journal of Materials in Civil*

Engineering, **27**(5): 04014158. 10.1061/(ASCE)MT.1943-5533.0001112

Tastan, E.O., Edil, T.B., Benson, C.H., and Aydilek, A.H. 2011. Stabilization of organic soils with

fly ash. *Journal of Geotechnical and Geoenvironmental Engineering*, **137**(9): 819-833. doi:

10.1061/(ASCE)GT.1943-5606.0000502

Tran, T.D., Cui, Y.J., Tang, A.M., Audiguier, M., and Cojean, R. 2014. Effects of lime treatment on

the microstructure and hydraulic conductivity of Héricourt clay. *Journal of Rock Mechanics*

and Geotechnical Engineering, **6**: 399-404. doi:10.1016/j.jrmge.2014.07.001

Verbrugge, J., De Bel, R., Correia, A., Duvigneaud, P., and Herrier, G. 2011. Strength and micro

observations on a lime treated silty soil. *In Proceedings of GeoHunan 2011: Road Materials and*

New Innovations in Pavement Engineering. Hunan China, 9-11 June 2011. American Society of

Civil Engineers, Reston, USA, pp. 89-96.

Vichan, S. and Rachan, R. 2013. Chemical stabilization of soft Bangkok clay using the blend of

calcium carbide residue and biomass ash. *Soils and Foundations*, **53**(2): 272-281. doi:

10.1016/j.sandf.2013.02.007

Wild, S., Abdi, M. R., and Leng-Ward, G. 1993. Sulphate expansion of lime-stabilized kaolinite: ii.

reaction products and expansion. *Clay Minerals*, **28**: 569-583.

693 **Table 1.** Properties of soils tested

Index	Value
Natural moisture content, w_n (%)	29.4
Specific gravity, G_s	2.73
Liquid limit, w_L (%) ^a	37.8
Plastic limit, w_P (%) ^a	19.9
Maximum dry density, $\rho_{d, \max}$ (g/cm ³) ^b	1.92
Optimum moisture content, w_{opt} (%) ^b	13.5
Particle size distribution (%) ^c	
Clay (< 0.002 mm)	13.6
Silt (0.002 to 0.074 mm)	83.9
Sand (> 0.074 mm)	2.5

694 ^a Based on ASTM D4318 (ASTM, 2010).

695 ^b Based on ASTM D698 (ASTM, 2012).

696 ^c Measured using a laser particle size analyzer Mastersizer 2000

697

698

699

700

Draft

701 **Table 2.** Major chemical compositions of the parent soil, CCR and quicklime used in this study ^a

Chemical composition	Soil (%)	CCR (%)	Quicklime (%)
CaO	1.3	68.99	68.54
SiO ₂	67.9	2.84	2.54
Al ₂ O ₃	14.1	2.16	1.0
MgO	2.5	0.12	0.34
Fe ₂ O ₃	5.0	0.15	0.62
SO ₃	0.01	0.76	0.11
Loss of ignition	5.19	24.85	26.51

702 ^a Measured using a X-ray Fluorescence Spectrometer.
703
704
705

706 **Table 3.** Basic physical and chemical properties of CCR and quicklime

Index	CCR	Quicklime
Specific gravity, G_s	2.32	3.21
Specific surface area (m^2/g) ^a	24.664	5.020
pH ^b	12.84	12.74
Particle size distribution (%) ^c		
Clay (< 0.002 mm)	4.2	3.9
Silt (0.002 to 0.074 mm)	67.6	37.8
Sand (> 0.074 mm)	28.2	58.3

707 ^a Measured using a Quantachrome Autosorb-iQ-AG automated gas sorption analyzer.

708 ^b Based on ASTM 4972 ([ASTM, 2013](#)).

709 ^c Measured using a laser particle size analyzer Mastersizer 2000.

Draft

Table 4. Summary of binder dosage, curing time, degree of compaction and number of identical samples for different tests in this study

Testing program	Binder dosage (%)	Curing time (day)	Degree of compaction (%)	Number of identical samples
Atterberg limits	0, 4, 6	28	NA ^h	1
PSD ^a	0, 4, 6	28	NA ^h	1
Compaction	0, 4, 6	0	NA ^h	1
UCS ^b	0, 4, 6	7, 28, 60, 120	93, 94, 96	3
CBR ^c	0, 4, 6	7, 28	93, 94, 96	3
M_r ^d	0, 4, 6	7, 28	94, 96	3
Soil pH	6	7, 28, 60, 120	100	1
XRD ^e	0, 6	180	100	1
TGA ^f	6	28, 120	100	3
MIP ^g	6	28, 60, 120	100	1

^a Particle size distribution

^b Unconfined compressive strength (UCS)

^c California Bearing ratio (CBR)

^d Resilient modulus

^e X-ray diffraction (XRD)

^f Thermogravimetric analyses (TGA)

^g Mercury intrusion porosimetry (MIP)

^h Not available

725 **Table 5.** Results of Atterberg limits tests for CCR and quicklime stabilized and unstabilized
726 soils

Soil	Binder content (%)	Curing time (d)	Liquid limit, w_L (%)	Plastic limit, w_p (%)	Plastic index, I_p
Untreated soil	0	NA ^a	37.8	19.9	17.9
CCR stabilized soils	4	28	42.7	29.6	13.1
	6	28	39.8	26.4	13.4
Quicklime stabilized soils	4	28	41.6	26.8	14.8
	6	28	44.3	28.8	15.5

727 ^a Not available

Draft

728 **Table 6.** Results of particle size distribution test

Soil	Binder content (%)	Curing time (d)	Clay-sized particle (< 2 μm) (%)	Silt-sized particle (2 to 74 μm) (%)	Sand-sized particle (74 to 2000 μm) (%)
Unstabilized soil	0	Not available	13.6	83.9	2.5
CCR stabilized soil	4	28	7.1	55.1	37.8
	6	28	3.8	35.5	60.7
Quicklime stabilized soil	4	28	10.0	63.6	26.4
	6	28	8.2	65.2	26.6

729

730

Draft

731 **Table 7.** The relative content of the hydration products

Hydration product	Range of water loss (°C)	CCR (%)		Quicklime (%)		Reference
		28 d	120 d	28 d	120 d	
CSH	50 to 200	1.861	2.108	1.804	1.98	HaHa et al. (2011)
CAH+CASH	200 to 300	0.95	1.01	0.86	0.864	HaHa et al. (2011)

732

733

Draft

List of Figure captions

Fig. 1 Particle size distributions of unstabilized soil, CCR and quicklime.

Fig. 2 Variations of q_u with curing time for soils with various degree of compaction: (a) 93%; (b) 94%; and (c) 96%.

Fig. 3 Variations of CBR with curing time and binder content for soils with various degree of compaction: (a) 93%; (b) 94%; and (c) 96%.

Fig. 4 Variations of resilient modulus (M_r) with degree of compaction and curing time for unstabilized soils and soils of 6% binder.

Fig. 5 Variations of soil pH with curing time.

Fig. 6 XRD diffractograms of unstabilized soil and CCR and quicklime stabilized soils.

Fig. 7 Thermogravimetric analysis (TGA) and differential thermogravimetric (DTG) analysis of soils stabilized with: (a) CCR at 28 d; (b) quicklime at 28 d; (c) CCR at 120 d; and (d) quicklime at 120 d.

Fig. 8 Summed content of C-S-H, C-A-H and C-A-S-H versus q_u of soils stabilized with CCR and quicklime (6% binder content).

Fig. 9 MIP test results for CCR and quicklime stabilized soils.

Fig. 10 Distributions of different types of pores in CCR and quicklime stabilized soils.

Fig. 1 Particle size distributions of unstabilized soil, CCR and quicklime.
172x122mm (300 x 300 DPI)

Fig. 2 Variations of q_u with curing time for soils with various degree of compaction: (a) 93%; (b) 94%; and (c) 96%.

203x146mm (300 x 300 DPI)

Fig. 3 Variations of CBR with curing time and binder content for soils with various degree of compaction: (a) 93%; (b) 94%; and (c) 96%.
214x156mm (300 x 300 DPI)

Fig. 4 Variations of resilient modulus (M_r) with degree of compaction and curing time for unstabilized soils and soils of 6% binder.
131x92mm (300 x 300 DPI)

Fig. 5 Variations of soil pH with curing time.
135x95mm (300 x 300 DPI)

Fig. 6 XRD diffractograms of unstabilized soil and CCR and quicklime stabilized soils.
251x356mm (300 x 300 DPI)

Fig. 7 Thermogravimetric analysis (TGA) and differential thermogravimetric (DTG) analysis of soils stabilized with: (a) CCR at 28 d; (b) quicklime at 28 d; (c) CCR at 120 d; and (d) quicklime at 120 d.
129x64mm (300 x 300 DPI)

Fig. 8 Summed content of C-S-H, C-A-H and C-A-S-H versus q_u of soils stabilized with CCR and quicklime (6% binder content).
128x90mm (300 x 300 DPI)

Fig. 9 MIP test results for CCR and quicklime stabilized soils.
137x95mm (300 x 300 DPI)

Fig. 10 Distributions of different types of pores in CCR and quicklime stabilized soils.
157x111mm (300 x 300 DPI)